

	<h1>TECHNICAL DATA SHEET</h1>	Realease	0 17.6.2019
		Nature of mod.	First issue
		Author	RQ
		Mod	CPO/ST Rev.2 del 17/06/2019

A.V.Saldature code T750  
 ISO 17672:2016 N.A.  
 EN 1044: N.A.  
 EN ISO 3677: B-74 Ag Cu Zn-740-780  
 AWS A 5.8: N.A.

Chemical Composition ( % )					
A.V.	Ag	Cu	Zn	Sn	Other elements
	Min. Max.	Min. Max.	Min. Max.	Min. Max.	Min. Max.
T750	73 75	18 19	7 9		

NOTE Maximum impurity limits applicable to all types are (% by mass) Al 0,001, Bi 0,030, P 0,008, Pb 0,025; total of all impurities = 0,15; total of all impurities for Ag 427, Ag 449 and Ag 485 = 0,30.

Working temperature: 780 °C  
 Melting range: 740°-780 °C  
 Specific gravity: 10 g/cm<sup>3</sup>

#### Characteristics / Applications:

Silver/copper alloy, with high silver contain, is ideal with copper but can be used also with steel, stainless steel and Ni alloys.

Heat sources:  
 Acetylene torch, air-gas torch, induction and resistance heating

Flux: D4, D26, D60, D70, D39H

### TECHNICAL SUPPLYING CONDITION ACCORDING WITH INTERNATIONAL STANDARD ISO 17672:2016

#### Availability

Rods	Coeted Rods	Wire	Foil	Perform	Powder	Paste
X	X	X	X	X	X	X